



Properties of Alloy 6019

Alloy 6019 was developed for use in machined cast on abutment/coping components used for dental implant restoration prostheses. The material composition of 60% Au, 19%Pt, 20% Pd, 1% Ir complies with all standard industry mechanical, physical and biocompatibility requirements for use of this alloy in the intended application.

Mechanical Properties of Alloy 6019 - Nominal		
Yield Strength		
Initial	ksi	135
Post 1,800 °F Burnout	ksi	93
Tensile Strength		
Initial	ksi	139
Post 1,800 °F Burnout	ksi	112
Hardness		
Initial	Knoop	278
Post 1,800 °F Burnout	Knoop	247
Modulus	x10 ⁶ psi	20
Physical Properties		
Melting Range	2,579° – 2,732° F	1415° – 1500° C
CTE	6.8 µin/in°F	12.3 µm/m°C
Biocompatibility	Extract	Result
Cytotoxicity ISO 10993-5	1X MEM	Pass
Intracutaneous Study ISO 10993-10	Sodium chloride	Pass

The information contained in this Data Sheet is intended to assist you in the use of this product. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular application. The user should determine the suitability of this material for each application. Data is subject to change without notice.

For More Information

[Contact Us to discuss your application with one of our Materials Specialists.](#)